

COMBUSTION CONTROL Ltd

266 Church Street Onehunga, Auckland ,NZ

www.combustioncontrol.co.nz .ph +6496341610

Product Data Sheet ID6262

Style - Size	GT132 - ½" X 1" OAW
Description	Medium Density Extruded Silicone Sponge "P" Seal
Temperature	500° (-100°) F/260° (-74 °) C
Application	Excellent choice for sealing doors, dampers and access panels where resiliency and clean ability is a premium. Widely used as a commercial seal for smokehouse and meat curing equipment. A good choice when operating conditions involve extremely low or high temperatures.
Chemical Resistance	Silicone is resistant to many acids and Chemicals except Benzene, Carbon Tetrachloride Chlorine, Petroleum Products, Paint Thinners and Lacquers (for specific product application information contact manufacturer).

